



**ACERO PARA FUNDICION DE DADOS A PRESION
COMPOSICION QUIMICA**

Grado	AISI	DIN	C	Mn	Si	Ni	Cr	Mo	V	VAD	VAR	Dureza*
DC®	H-13	1.2344	0.4	0.35	1	-	5.25	1.5	1	¢		Ann – 52 HRc
DC® - Xtra Premium	H-13	1.2344	0.4	0.35	1	-	5.25	1.5	1	¢	¢	Ann – 54 HRc
ShelleX®		1.2367	0.36	0.6	0.9	-	5	2.85	0.25	¢		Ann – 56 HRc
ShelleX®Premium		1.2367	0.36	0.35	0.9	-	5	2.85	0.25	¢	¢	Ann – 56 HR

© Copyright Finkl de México S. de R.L. de C.V. 2006 | Todos los derechos reservados