



**ACERO PARA TRABAJO EN CALIENTE
COMPOSICION QUIMICA**

Grado	AISI	DIN	C	Mn	Si	Ni	Cr	Mo	V	VAD	Dureza*
FX®		1.2714	0.47	0.9	0.35	0.8	1.5	0.4	0.04	¢	24 – 50 HRc
WF®		-	0.42	0.75	0.45	0.8	2.5	1	0.03	¢	24 . 50 HRc
DC®	H-13	1.2344	0.4	0.35	1	-	5.25	1.5	1	¢	24 . 54 HRc
ShelleX® Press		1.2367	0.36	0.6	0.9	-	5	2.85	0.25	¢	24 . 54 HRc
Die®		-	0.2	0.7	0.25	3.25	-	3.35	-	¢	35 – 48 HRc
HMX	-	-	0.47	0.4	0.8	-	7.55	1.4	1.4	¢	X

© Copyright Finkl de México S. de R.L. de C.V. 2006 | Todos los derechos reservados